

## Electronic and Electric UL Registration Chart

### Status of UL Registration

E52579 (M)

Mtl Dsg	Col	Min Thk mm	UL94 Flame Class	RTI			H W I	H A T	H V T R	D 4 9 5	C T I
				Elec	Mech						
					with Imp	w/o Imp					
Glass fiber reinforced polyamide (PA) designated "ARLEN", furnished in the form of pellets.											
C215(e)	All	0.75	94HB	65	65	65	-	-	-	-	-
C2(d)(e)											
C240(e)	All	0.75	94HB	65	65	65	-	-	-	-	-
		1.5	94HB	115	95	115	-	-	-	-	-
		3.0	94HB	115	105	115	-	-	-	-	-
C215N(e)	All	0.80	94V-0	65	65	65	-	-	-	-	2
C230N(e)	All	0.80	94V-0	65	65	65	-	-	-	-	-
		3.0	94V-0	65	65	65	-	-	-	-	2
C240N(e)	All	0.80	94V-0	65	65	65	0	0	-	-	-
		1.5	94V-0	120	105	115	0	0	-	-	-
		3.0	94V-0	120	115	125	0	0	1	6	1
※ CH230N(e)	All	0.80	94V-0	130	90	125	-	-	-	-	-
		1.5	94V-0	130	120	125	-	-	-	-	-
		3.0	94V-0	130	120	125	-	-	-	-	1
CH245N(e)	All	0.80	94V-0	130	120	125	-	-	-	-	-
		3.0	94V-0	130	120	125	-	-	-	-	1

(d) Represents the percentage of glass content by two digits 16-39 incl.

(e) With or without one or two letters A-ZZ incl. except N.

※ Re grind 50% 0.80 94V-0