

Grades and Physical Properties Chart - Mechanical, Structural and Tribological Applications

				Test method	A/G Series (For mechanical)		R	L	E	N		Remarks		
					and structural	parts)	A/E (For	Series tribolic	non-reinforced, flameretardant	applications)				
Physical Properties			Unit	ASTM	A315	A335	A350	G335	AE4200	AE4200N	AE2230	PA66	PA MXD6	PPS
Glass fiber content		%	-		15	35	50	35	0	0	30	30	40	40
Specific gravity		-	D792		1.30	1.48	1.63	1.47	1.10	1.40	1.37	1.37	1.53	1.67
Mechanical Properties														
Tensile strength	dry	MPa	D638		120	240	300	200	80 ³	70 ³	200	180	220	170
	(moist) ^{*1}				(110)	(220)	(270)	(180)	(70) ³	(60) ³	(180)	(130)	(150)	(-)
Tensile elongation	dry	%	D638 ^{*2}		3	3	3	3	50 ³	4 ³	4	4	2	2
	(moist) ^{*1}				(3)	(3)	(3)	(3)	(50) ³	(4) ³	(4)	(4)	(2)	(-)
Flexural strength	dry	MPa	D790		190	360	430	340	110	120	270	260	310	250
	(moist) ^{*1}				(170)	(320)	(390)	(310)	(100)	(110)	(240)	(180)	(210)	(-)
Flexural modulus	dry	MPa	D790		6,000	12,000	17,000	11,000	2,400	3,000	9,000	8,800	13,000	13,000
	(moist) ^{*1}				(5500)	(11,000)	(15,000)	(10,000)	(2,200)	(2,700)	(8,000)	(6,000)	(11,000)	(-)
Izod impact strength	dry	J/m	D256		50	130	150	100	200	70	100	130	80	80
(notched)	(moist) ^{*1}				(70)	(150)	(160)	(120)	(220)	(80)	(110)	(150)	(80)	(-)
Rockwell hardness		M scale	D785		105	110	110	-	65 (R110)	80	95	95	95	100
Thermal Properties														
Melting point		°C	-		320	320	320	300	320	320	320	260	240	280
Glass transition point		°C	-	D648	125	125	125	140	125	125	125	50	80	90
Deflection temp. under load (1.82MPa)		°C	D648		290	310	310	280	135	145	300	255	230	265
Coefficient of linear thermal expansion	Flow direction Vertical direction	X10 ⁻⁵ /°C	D696		3.4 5.5	2.0 4.5	1.8 4.2	-	8.0 8.2	6.5 6.7	2.6 6.0	2.2 9.0	2.0 4.5	2.0 4.0
Electrical Properties														
Volume resistivity	(dry)	Ω • cm	D257		10 ¹⁶	10 ¹⁶	10 ¹⁶	10 ¹⁶	10 ¹⁶	10 ¹⁵	10 ¹⁶	10 ¹⁵	10 ¹⁶	10 ¹⁶
Dielectric constant (10 ⁶ Hz)	(dry)	-	D150		4.2	4.5	4.5	-	3.3	3.3	3.7	3.3	4.0	3.8
Dielectric dissipation factor (10 ⁶ Hz)	(dry)	-	D150		0.020	0.018	0.018	-	0.018	0.014	0.018	0.015	0.009	0.0014
Dielectric breakdown voltage	(dry)	kV/mm	D149		25	27	29	28	23	31	27	23	31	17
Other Properties														
Mold shrinkage (2mmt)	Flow direction Vertical direction	%	D955		0.5 0.6	0.3 0.6	0.2 0.6	0.2 0.5	0.9 0.9	0.8 1.0	0.4 0.7	0.4 0.8	0.2 0.6	0.2 0.4
Water absorption (24 hr in water) (2mmt)	23°C	%	D570		0.4	0.3	0.2	0.3	0.4	0.3	0.2	0.8	0.2	0.02
	100°C	%			2.5	1.8	1.2	1.7	2.6	2.0	1.7	4.5	3.2	0.3
Flammability		-	UL94	H B	H B	HBequiv.	HBequiv.	H B	V-0	HBequiv.	H B	H B	V-0	

Notes:

The above figures are just representative values but not specification values.

*1 Moist: In a saturated state in the atmosphere at 23°C and a relative humidity of 65%

*2 Elongation was measured between the chucks.

*3 Test specimens of the non-reinforced grades were 2 mm.

Unit conversion:

Tensile strength, flexural strength,
flexural modulus.

1 MPa = 10.2 kg/cm²

Izod impact strength.
1 J/m=0.102 kg • cm/cm