## SYNTEX<sup>TM</sup> Data Sheet

Grades	Basis weight (g/m²)	Fiber diameter	Thickness (mm)	Tensile strength (N/50mm)		Elongation (%)		Air permeability (cc/cm²/s)
		(μm)		MD	CD	MD	CD	
PS-103	16	20	0.22	35	12	40	40	N/A
PS-104	20	20	0.25	40	25	40	40	360
PS-105	25	20	0.29	55	35	40	45	300
PS-106	30	20	0.33	70	40	40	50	270
PS-108	40	20	0.38	100	45	40	50	200
PS-110	50	20	0.43	120	50	40	50	170
PS-112	60	20	0.48	135	60	35	50	140
PS-114	70	20	0.51	150	62	35	45	110
PS-116	80	20	0.55	160	65	35	45	80
PS-120	100	20	0.60	185	70	30	40	50
PK-102	13	30	0.19	20	12	80	90	N/A
PK-103	15	30	0.20	25	13	60	70	N/A
PK-108	40	30	0.38	90	35	40	60	330



\*Test method: JIS L 1913

## ABOUT MITSUI CHEMICALS AMERICA, INC

Mitsui Chemicals America, Inc. produces and supplies specialty chemicals and high performance polymers to North and South American markets. We offer a broad range of Chemicals & Intermediates, Chemicals Solvents, Specialty Polymers and Engineering Plastics, Functional Materials, Electronic Materials, and Adhesive Resins. The company's product lines are marketed in cooperation with its parent company, Mitsui Chemicals, Inc. and its global affiliate network. Mitsui Chemicals, Inc., a leading company in the global chemicals industry, is committed to contributing to society by providing innovative, high quality products and services to customers, and creating materials that maintain harmony with the environment. Please visit us online at:

DISCLAIMER: The information contained in this brochure is, to the best of our knowledge, accurate and reliable, but all suggestions are made without warranty, either express or implied. The values relevant to properties or the like of the product stated herein were obtained using laboratory test specimens prepared in Mitsui Chemicals, Inc. laboratories and are not to be used as product specifications, nor assumed to be identical to values obtained on the finished product manufactured by our customers. Nothing herein shall be construed as permission or as recommendation for uses which infringe valid patents or as extending a license under valid patents. Because the conditions and methods of use on the part of our customers are beyond our control, Mitsui Chemicals America, Inc. disclaims any liability incurred in connection with the use of our products.

