

Evaluation as a Coating Primer

| Substrate | P-501 | Non-Coat |
|-----------|-------------------------------|------------------|
| PA6 | 810 (100/100) | 70 (0/100) |
| PBT | 900 (100/100) | 400 (100/100) |
| PPO | 300 (100/100) | 50 (0/100) |
| EPDM | Material Failure (100/100) | 200 (35/100) |

Peeling Test Condition: 180° , 50mm/min,
Unit: g/cm

(Cross Cut Adhesion Test)