

Evaluation as a Coating Primer

©2023 Mitsui Chemicals, Inc.

	Substrate	Polypropylene	TPE
Adhesion	Cross Cut Adhesion Test	100/100 (450)	100/100 (600)
Water -resistance	40°C, 240hr	100/100	100/100
Humidity -resistance	50°C, R.H. 98% 240hr	100/100	100/100
Saltwater -resistance	NaCl3% Solution 40°C, 96hr	100/100	100/100
Thermal -resistance	80°C, 400hr	100/100	100/100

Cross Cut Adhesion Test
(Peeling Test Condition: 180° , 50mm/min, Unit: g/cm)